

**IN THE SPECIFICATION**

Page 75, please replace Table 1 with the following new Table.

TABLE 1

	K1	K2	Ex. 1	Ex. 2	Ex. 3	Ex. 4	Comp. Ex. 1	Comp. Ex. 2
Carbon black	2.5	0.8	0.2	0.12	0.2	0.2	0.2	0.2
Pigment Blue 60	-	-	-	0.1	0.1	-	-	-
Water-soluble resin (dispersant)	1.3	0.4	0.1	0.1	0.15	0.1	0.1	0.1
pH-adjusted resin emulsion A (solid content: [33%] 15%)	-	2	13.3	13.3	13.3	33.5	6.7	-
AQ 593 (solid content: 30%)	-	6.7	9.9	9.9	-	-	6.7	9.9
AQ 513 (solid content: 33%)	-	-	-	-	10	-	-	-
HS500 (a product of HAYASHIBARA SHOJI Inc.)	2	5	5	6	4	2	5	5
Glycerol	18	19	17	15	18	16	20	21
Triethanolamine	0.9	0.9	0.9	-	0.9	0.6	0.9	0.9
Tripipanalamine	-	-	-	0.5	-	-	-	-
1,2-Hexanediol	5	5	5	5	-	5	5	5
Triethylene glycol monobutyl ether	-	-	-	-	5	-	-	-
Sarfinol 465	-	-	-	-	1	-	-	-
BYK348	0.5	0.5	0.5	0.5	-	0.5	0.5	0.5
Proxel GXL	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
EDTA	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02